



Embossing Grade Physical Property Averages

| Thickness | Target Density (lbs. per sq. ft) | Target IB (psi) | MOR (psi) | MOE (psi) | Face Screw Holding (lbs.) | Edge Screw Holding (lbs.) |
|-----------|----------------------------------|-----------------|-----------|-----------|---------------------------|---------------------------|
| 1/2" | 42.0 | 130 | 4000 | 340,000 | 225 | - |
| 5/8" | 42.0 | 130 | 3300 | 340,000 | 225 | 200 |
| 3/4" | 42.00 | 120 | 3300 | 340,000 | 225 | 200 |